

SOPREMAPOOL PVC LIQUID

DESCRIPTION

Polyvinylchloride in tetrahydrofuran (THF). High sealing strength for PVC membranes. Flammable liquid. Easy to apply with the suitable dispenser.

STORAGE

Can of 1 kg. The minimum shelf life is 3 years, in original unopened packaging, stored in a dry and cool place. In case of a slight decrease in fluidity, it is possible to restore it with a small addition of THF and mixing well.

INSTALLATION

The product is used for cold sealing the welded edge of SOPREMAPOOL membranes. See welding instructions on the technical prescriptions of the SOPREMAPOOL-membranes. The consumption is approximately 10 g/m weld.

HANDLING

Avoid contact with polystyrene.
Do not apply on damp waterproofing membranes.
Follow the instructions and dispositions on the label and in the safety data sheet of the product.
Contact Soprema for information.

COLOURS

Transparent, Light Blue, Azure Blue, Sapphire Blue, Dark Blue, Caribbean Green, Natural Green, Moss Green, Sand, White, Light Gray, Medium Gray, Basalt Gray, Black, Bali Sand, Wood, Sensitive Sand, Sensitive Sahara, Sensitive Vanilla and Sensitive Infinite/Rock. For complete and updated variants see the SOPREMAPOOL brochure.

SAFETY INFORMATION

For more information, please refer to the relevant safety data sheet.

SOPREMA always recognises as a high level of importance the quality of the products, the environment and safety. For this reason, we operate independently monitored Quality and Environment Assurance Systems in line with **EN ISO 9001** and **EN ISO 14001**.

CHARACTERISTICS	STANDARD	UNIT	VALUE
Colour			various
Aspect			viscous liquid
Density at 20 °C		g/cm ³	0,98
Ignition temperature	DIN 51755	°C	-21

